

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
22 November 2001 (22.11.2001)

PCT

(10) International Publication Number
WO 01/87573 A1

(51) International Patent Classification⁷: **B29C 49/18,**
49/48

(21) International Application Number: PCT/IB00/00675

(22) International Filing Date: 19 May 2000 (19.05.2000)

(25) Filing Language: English

(26) Publication Language: English

(71) Applicant and

(72) Inventor: LIMANJAYA, Tjandra [ID/ID]; Jl. Kaji No.
1B-BA, Petojo Utara, Jakarta Pusat 10730 (ID).

KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD,
MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD,
SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ,
VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG,
CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).


Published:

— with international search report

(81) Designated States (*national*): AE, AL, AM, AT, AU, AZ,
BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE,
ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP,

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: PLASTICS CONTAINER WITH INTEGRAL HANDLE



(57) Abstract: A method of forming a plastics material container having a hollow handle and a finger aperture between the handle and a main body of the container, the method consisting in the steps of: blowing a heated, injection moulded preform to a preliminary shape in a preliminary blow mould; separating the preliminarily shaped container from the preliminary mould; re-heating the preliminarily shaped container to elevated temperature; moving together the preliminarily shaped container to a secondary blow mould for imparting finish formed shape to the container, the secondary mould impressing concavity into the container in the region of the finger aperture; blowing the heated, preliminarily shaped container in the secondary mould to impart the finish formed shape to the container; separating the container from the secondary mould; welding together opposite side walls of the container around the finger aperture; and cutting out the finger aperture.



WO 01/87573 A1

PLATIC CONTAINER WITH INTEGRAL HANDLE

The present invention relates to a plastics material container, in particular a P.E.T. container with a hollow handle.

5

For bottles in excess of one litre in capacity, it is preferable to be able to provide the bottle with an integral handle. Bottles made of polyethylene can be provided with integral hollow handles by the extrusion blow moulding process. However, this process is not suitable for bottles of polyethylene terephthalate – P.E.T. Nevertheless, P.E.T. is a preferred food grade material for bottles, being FDA approved.

10

P.E.T. bottles can be provided with handles. However these are usually separate mouldings, which are made before the bottle and fitted into the blow mould. This is an inconvenient and expensive process. For cheapness of the bottle, the handle is often of a cheaper material. However, this makes for inconvenience in reprocessing of used bottles. An alternative is to produce a handle of P.E.T. as an integral moulding with a preform, from which the bottle is injection blow moulded. Such bottles are expensive in terms of usage of heavier material.

20

The object of the present invention is to provide an improved P.E.T. container, that is with a hollow handle.

According to the invention there is provided a method of forming a plastics material container having a hollow handle and a finger aperture between the handle and a main body of the container, the method consisting in the steps of:

25

30

- blowing a heated, injection moulded preform to a preliminary shape in a preliminary blow mould;
- separating the preliminarily shaped container from the preliminary mould;
- re-heating the preliminarily shaped container to elevated temperature;
- bringing together the preliminarily shaped container and a secondary blow mould for imparting finish formed shape to the container, the secondary mould impressing concavity into the container in the region of the finger aperture;

CONFIRMATION COPY

- blowing the heated, preliminarily shaped container in the secondary mould to impart the finish formed shape to the container;
- separating the container from the secondary mould;
- welding together opposite side walls of the container around the finger aperture; and
- cutting out the finger aperture.

In this specification, the term "preliminary shape" means a shape which is close to but distinct from the finish formed shape. In particular, the preliminary shape has overall dimensions which are generally similar to those of the finish formed shape. The preliminary shape is generally convex including at the finger aperture position; whilst the finish formed shape has concavity at the finger aperture (even although locally the container may be convex over its entire surface). The term "finish formed shape" is believed to be self-explanatory in referring to the final shape of the container.

The secondary mould in imparting the finger aperture concavity can bring the opposite side walls into contact around the concavity. Alternatively, the side walls may remain spaced, albeit closely, in the secondary mould and be actually abutted at the welding step.

Whilst it can be envisaged that the two blow mould steps and the re-heating step could all occur at the same station, for instance with one pair of mould parts approaching on one axis, the other pair approaching on an orthogonal axis and the heater approaching on a third orthogonal axis; the preform, preliminary bottle and finish formed bottle are preferably processed at sequential stations. Alternatively, it is envisaged that the three could be processed quite separately from each other at unrelated stations.

The welding step is preferably performed by bring opposed heated platens into contact with the opposite side walls at the finger aperture sufficiently firmly and at sufficient temperature to weld them together. Alternatively, the platens can be ultrasonically or otherwise excited for the welding.

The blowing of the preliminary container in the secondary mould is preferably performed with cold air at elevated pressure to ensure a good reproduction of the mould shape in the container and to cool the container below its solidification temperature. By "solidification temperature" is intended the temperature at or below which the container retains its finish formed shape in ambient temperature. Preferably the application of cold, high pressure air followed after initial circulation of heated air inside the container on closure of the secondary mould to maintain plasticity of the container, whilst the secondary mould is being closed.

10

The method of the invention is particularly applicable to forming containers, including bottles, out of P.E.T. For this, the re-heating step is typically to approximately 180°C.

According to another aspect of the invention there is provided a P.E.T. container comprising a hollow handle and a finger aperture between the handle and a main body of the container.

The internal space of the handle and the internal space of the main body of the container communicate with each other, whereby liquid contents of the container can flow from the main body into the handle.

20

According to a third aspect of the invention there is provided blow moulding equipment including:

- a preliminary blow mould for blowing a preform into a preliminarily shaped container;
- means for re-heating the preliminarily shaped container to elevated temperature;
- a secondary blow mould for imparting finish formed shape to the container, the secondary mould having:
 - projecting portions of the mould which deform the side walls of the preliminarily shaped container to form the handle, a region of the main body

25

30

around the finger aperture and portions of the side walls within the finger aperture.

To help understanding of the invention, a specific embodiment thereof will
5 now be described by way of example and with reference to the accompanying drawings, in which:

Figure 1 is a front view of a P.E.T. bottle according to the invention;

Figure 2 is a cross-sectional side view of a preform for the bottle of Figure 1;

Figure 3 is a similar view of the preform blown to preliminary shape in a
10 preliminary blow mould;

Figure 4 is a similar view of the preliminarily shaped bottle being reheated;

Figure 5 is a similar view of the preliminarily shaped bottle being secondarily
blown in a secondary mould;

Figure 6 is a scrap transverse view on the line VI-VI in Figure 5, but on a
15 larger scale and in the region of a finger aperture, of the bottle in the secondary
mould;

Figure 7 is a cross-sectional transverse view of the bottle being heat sealed at
the finger aperture;

Figure 8 is a similar view of the finger aperture being cut

20 Figure 9 is a side view of the finish formed bottle.

Referring first to Figure 1, the P.E.T. bottle 1 there shown has a main body 2
and a handle 3. Between the handle and the body, the bottle has a finger aperture 4,
allowing a user's fingers to pass round and grip the handle. The bottle has a
25 conventional neck 5 for a cap. On a central plane of the bottle and the handle, the
opposite side walls 6 are welded together 7 around the finger aperture.

Now referring to the rest of the Figures, the starting point for the bottle 1 is an
injection moulded preform 11, see Figure 2. This is heated, positioned in a
30 preliminary mould 12 and blown to a preliminary shape 14 of the bottle. The
preliminary bottle is removed from preliminary mould. These steps – injection
moulding, heating, blow moulding and removal from the mould – are all conventional
in the blow moulding of P.E.T. bottles, except insofar as conventionally they result in

an end product. In accordance with the present invention, the preliminary bottle is an intermediary product.

Next, it is set up in a heating station, where it is heated by radiant heaters 21, see Figure 4. They heat the preliminary bottle to $180^{\circ}\text{C} \pm 20^{\circ}$. It is moved to a secondary mould 31. At the mould, the neck 5 is supported by a neck ring 32 and a blow pin 33 is advanced into the preliminary bottle 14 as the mould 31 is closed. During closure, heated air typically at the preheat temperature of the bottle, i.e. $180^{\circ}\text{C} \pm 20^{\circ}$, is passed through the blow pin 33 at a pressure insufficient to blow the bottle, typically 0.5bar. As the mould closes, the preliminary bottle is contacted by projecting portions 34 of the mould 31 which form the handle 3, the region of the main body 20 around the finger aperture 4 and the portions 40 of the side walls within the finger aperture. Thus the projecting portions deform a region of the preliminary bottle which was universally convex, into one which has two concavities, namely the portions 35 on opposite sides including the handle 3, the finger aperture portions 40 and the main body region 20. It should be noted that when the portions 40 are cut out – see below – the resulting surface of the bottle will be primarily, locally convex.

Once the mould is fully closed, which preferably leaves the opposite portions 40 abutting each other, the warm air flow is replaced by a high pressure cold air flow, typically at 30bar. This blows the bottle to its finish formed shape. The side walls come into firm contact with that the walls of the mould, which in combination with the cold air solidifies the walls. Thus when the secondary mould is opened, the bottle retains its finish formed shape.

25

The bottle 1 is then moved to a sealing station, see Figure 7, where opposed heated platens 41 abut the finger aperture portions 40, particularly firmly around their edges. The side walls are thus sealed/welded to each around these edges. The bottle is moved again to a cutting station, see Figure 8, where opposed knife and die block members 51 cut the portions 40 from the handle 3 and the main body 20. This completes the formation of the bottle.

30

The invention is not intended to be restricted to the details of the above described embodiment. For instance, the container could be larger than a bottle and provided with two handles, one on either side. Also it could be a drum or the like with a top handle.

CLAIMS:

1. A method of forming a plastics material container having a hollow handle and a finger aperture between the handle and a main body of the container, the method consisting in the steps of:

- 5 • blowing a heated, injection moulded preform to a preliminary shape in a preliminary blow mould;
- separating the preliminarily shaped container from the preliminary mould;
- re-heating the preliminarily shaped container to elevated temperature;
- 10 • bringing together the preliminarily shaped container and a secondary blow mould for imparting finish formed shape to the container, the secondary mould impressing concavity into the container in the region of the finger aperture;
- blowing the heated, preliminarily shaped container in the secondary mould to impart the finish formed shape to the container;
- separating the container from the secondary mould;
- 15 • welding together opposite side walls of the container around the finger aperture; and
- cutting out the finger aperture.

2. A method as claimed in claim 1, wherein the secondary mould in imparting the finger aperture concavity brings the opposite side walls into abutting contact
20 around the concavity.

3. A method as claimed in claim 1, wherein the secondary mould in imparting the finger aperture concavity leaves the side walls closely spaced and the side walls are actually abutted subsequently at the welding step.

4. A method as claimed in claim 1, claim 2 or claim 3, wherein the preform,
25 preliminary bottle and finish formed bottle are processed at sequential stations.

5. A method as claimed in claim 1, claim 2 or claim 3, wherein the preform, preliminarily shaped container and the finish formed container are processed at separate stations.

6. A method as claimed in any preceding claim; wherein the welding step is
30 performed by bring opposed welding platens into contact with the opposite side walls at the finger aperture sufficiently firmly and at sufficient temperature to weld them together.

7. A method as claimed in claim 6, wherein the welding platens are heated platens.
8. A method as claimed in claim 6, wherein the welding platens are ultrasonically excited platens.
- 5 9. A method claim as claimed in any preceding claim, wherein the blowing of the preliminary container in the secondary mould is performed with cold air at elevated pressure for reproduction of the mould shape in the container and to cool the container below its solidification temperature.
- 10 10. A method as claimed in claim 9, including, in a step prior to application of cold, high pressure air, initial circulation of heated air inside the container on closure of the secondary mould to maintain plasticity of the container whilst the secondary mould is being closed.
11. A method as claimed in any preceding claim, wherein the container is of P.E.T. material and the re-heating step is to $180^{\circ}\text{C} \pm 20^{\circ}$.
- 15 12. A P.E.T. container comprising a hollow handle and a finger aperture between the handle and a main body of the container.
13. A blow moulding equipment for performing the method of any one of claims 1 11, including:
- a preliminary blow mould for blowing a preform into a preliminarily shaped container;
 - means for re-heating the preliminarily shaped container to elevated temperature;
 - a secondary blow mould for imparting finish formed shape to the container, the secondary mould having:
 - 25 • projecting portions of the mould which deform the side walls of the preliminarily shaped container to form the handle, a region of the main body around the finger aperture and portions of the side walls within the finger aperture.

FIG.1




FIG.2





FIG.3



2/4

FIG. 5




FIG. 4




FIG. 7







FIG. 6



SUBSTITUTE SHEET (RULE 26)

4/4



INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 00/00675

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 B29C49/18 B29C49/48

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 B29C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)
EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 038 006 A (FARRELL JOHN J) 26 July 1977 (1977-07-26)	1,2,4-7
Y	claim 1; figures 1,2	3,8,9,11
Y	EP 0 346 518 A (TAHARA SHOYEI CO LTD ;TOA GOSEI CHEM IND (JP)) 20 December 1989 (1989-12-20) column 1, line 1 - line 6 column 2, line 5 - line 8 column 3, line 38 - line 56 column 5, line 58 - column 6, line 34 column 7, line 14 - line 44; figures 1-4	3,8,11
X	US 4 657 502 A (RYDMANN THEO) 14 April 1987 (1987-04-14)	13
A	column 1, line 1 - line 16; claim 1	1,11
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

15 January 2001

Date of mailing of the international search report

23/01/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5618 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Ingelg rd, T.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/IB 00/00675

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 178 816 A (SUZUKI SABURO ET AL) 12 January 1993 (1993-01-12) column 4, line 15 - line 23; claim 1	1, 5, 11, 13
Y	US 4 318 882 A (AGRAWAL PURUSHOTTAM D ET AL) 9 March 1982 (1982-03-09) abstract column 1, line 1 - line 15 column 12, line 3 - line 6	9

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/IB 00/00675

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4038006	A	26-07-1977	US 3928522 A	23-12-1975
EP 0346518	A	20-12-1989	JP 1929455 C	12-05-1995
			JP 6035150 B	11-05-1994
			JP 63222835 A	16-09-1988
US 4657502	A	14-04-1987	DE 3314106 A	25-10-1984
			FR 2544655 A	26-10-1984
			GB 2138735 A, B	31-10-1984
US 5178816	A	12-01-1993	JP 1958896 C	10-08-1995
			JP 4161304 A	04-06-1992
			JP 6088315 B	09-11-1994
US 4318882	A	09-03-1982	NONE	